

June 1965

GA-724

Brief 65-10172

NASA TECH BRIEF



NASA Tech Briefs are issued by the Technology Utilization Division to summarize specific technical innovations derived from the space program. Copies are available to the public from the Clearinghouse for Federal Scientific and Technical Information, Springfield, Virginia, 22151.

Aluminum Alloys Protected Against Stress-Corrosion Cracking

The problem: To minimize stress-corrosion cracking in aluminum alloys subjected to sustained surface stresses and corrosive environments.

The solution: Appropriate surface treatments and application of protective coatings.

How it's done: The most effective protection is obtained by applying a topcoat of epoxy-polyamide paint to shot-peened or 5- to 7-mil-thick metallized surfaces of the aluminum alloy. Satisfactory temporary protection is afforded by a 3- to 4-mil-thick electroplated galvanic coating, or a topcoat of paint containing epoxy-polyamide or polyurethane resins. The epoxy-polyamide paint is the better of the two paints for this application and can be used on unprimed surfaces. Care is necessary to prevent breaking or scratching the paint film. When severe corrosive environments are not encountered, shot peening alone can provide good surface protection, provided all exposed surfaces are treated.

Notes:

1. Anodic films and zinc-rich paint were found to be the least effective coatings for preventing stress-corrosion cracking.
2. Further information on the control of stress corrosion in aluminum alloys is given in ALCOA Technical Paper No. 17, "Resistance of Wrought High-Strength Aluminum Alloys to Stress Corrosion", Aluminum Corporation of America, Pittsburgh, Pennsylvania. Inquiries may also be directed to:
Technology Utilization Officer
Marshall Space Flight Center
Huntsville, Alabama, 35812
Reference: B65-10172

Patent status: NASA encourages commercial use of this innovation. No patent action is contemplated.

Source: ALCOA Research Laboratories under contract to Marshall Space Flight Center (M-FS-235)

Brief 65-10172

Category No. 03

This document was prepared under the sponsorship of the National Aeronautics and Space Administration. Neither the United States Government, nor NASA, nor any person acting on behalf of NASA: A. Makes any warranty or representation, express or implied, with respect to the accuracy, completeness, or usefulness of the information contained in

this document, or that the use of any information, apparatus, method, or process disclosed in this document may not infringe privately-owned rights; or B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of, any information, apparatus, method, or process disclosed in this document.